



Product General Specifications

Base Material	Cross-linked polyolefin, Mylar .004" overlay	
Thickness	2mm (.080")	Finished thickness
MVTR	0.31 lbs / 1000 Sq. Ft. per 24hrs	(Moisture barrier spec)
R Value	3	(Thermal resistance)
Compression	29% @ 10.5 PSI	(Resistance to compression)
Tensile Strength	200 PSI	(Breaking force required)
Tear resistance	28.0 lbs/in	(Notched Breaking force)
IIC	75 *	
STC	73 *	

*See " STC& IIC Straight talk" publication included in dealer info binders, on our website or call our sales team for assistance.

Product Standard Packaging Spec's

Master Packs **43" x 335 Lin Ft. (1200 Sq. Ft.) 4 Per Pallet 4800 S.F.**

100' Rolls **43" x 28 Lin Ft. (1200 Sq. Ft. / Box) 4 Per Pallet 4800 S.F.**

Weight **120 lbs / Pallet**

Trademark International
 20665 93 Ave. Langley, BC. Canada
 800-526-5107

www.trademarkinternational.com